

AMENDMENTS TO THE CLAIMS

The following listing of claims will replace all prior versions, and listings, of claims in the application:

LISTING OF CLAIMS:

1. (Currently amended): A polarizing element comprising a reflective polarizing plate comprising a circularly-polarized light separation plate for separating incident natural light into reflected light and transmitted light both of which are composed of polarized light, a retardation plate, and a light-diffusion pressure-sensitive adhesive layer ~~provided to the reflective polarizing plate~~ interposed between the circularly-polarized light separation plate and the retardation plate.

2. (Canceled)

3. (Currently amended): The polarizing element according to claim 2 ~~1~~, wherein the circularly-polarized light separation plate comprises a cholesteric liquid crystal layer.

4. (Previously presented): The polarizing element according to claim 3, wherein the cholesteric liquid crystal layer is a liquid crystal polymer layer that is Grandjean-oriented on a transparent polymer substrate via an orientation film.

5. (Previously presented): The polarizing element according to claim 4, wherein the cholesteric liquid crystal layer has a superimposed structure of cholesteric liquid crystal layers different from each other in a helical pitch of the Grandjean orientation.

6. (Currently amended): The polarizing element according to claim 2 ~~1~~, wherein the retardation plate is a quarter wavelength plate.

7. (Canceled)

8. (Original): The polarizing element according to claim 1, wherein the light-diffusion pressure-sensitive adhesive layer is made of a polymer containing uncolored transparent particles.

9. (Original): The polarizing element according to claim 8, wherein the polymer is an acrylic polymer having a weight average molecular weight of at least 100,000.

10. (Original): The polarizing element according to claim 8, wherein the uncolored transparent particles having an average particle diameter ranging from 0.5 μm to 20 μm are selected from inorganic particles and organic particles.

11. (Original): The polarizing element according to claim 1, wherein the light-diffusion pressure-sensitive adhesive layer is provided adjacent to the reflective polarizing plate.

12. (Currently amended): A liquid crystal display having a polarizing element comprising a reflective polarizing plate comprising a circularly-polarized light separation plate for separating incident natural light into reflected light and transmitted light both of which are composed of polarized light, a retardation plate, and a light-diffusion pressure-sensitive adhesive layer ~~provided to the reflective polarizing plate~~ interposed between the circularly-polarized light separation plate and the retardation plate.

13. (Currently amended): A method of manufacturing a polarizing element, wherein the polarizing element comprises a reflective polarizing plate comprising a circularly-polarized light separation plate for separating incident natural light into reflected light and transmitted light both of which are composed of polarized light, and a retardation plate, ~~and said method comprising interposing~~ a light-diffusion pressure-sensitive adhesive layer provided to the reflective polarizing plate between the circularly-polarized light separation plate and the retardation plate.

14. (Original): The method according to claim 13, wherein the light-diffusion pressure-sensitive adhesive layer is provided adjacent to the reflective polarizing plate.

15. (Canceled)

16. (Original): The method according to claim 13, wherein the light-diffusion

pressure-sensitive adhesive layer is made of a polymer containing uncolored transparent particles.

17. (Original): The method according to claim 16, wherein the polymer is an acrylic polymer having a weight average molecular weight of at least 100,000.

18. (Original): The method according to claim 16, wherein the uncolored transparent particles having an average particle diameter ranging from 0.5 μm to 20 μm are selected from inorganic particles and organic particles.

19. (Previously presented): The polarizing element according to claim 1, wherein the reflective polarizing plate comprises a linearly-polarized light separation plate.

20. (Previously presented): The polarizing element according to claim 1, wherein the reflective polarizing plate is a circularly-polarized light separation plate.

21. (Currently amended): The polarizing element according to claim ~~19~~ 20, wherein the circularly-polarized light separation plate comprises a cholesteric liquid crystal layer.

22. (Currently amended): The polarizing element according to claim ~~20~~ 21, wherein the cholesteric liquid crystal layer is a liquid crystal polymer layer that is Grandjean-oriented on a transparent polymer substrate via an orientation film.

23. (Currently amended): The polarizing element according to claim ~~21~~ 22, wherein the cholesteric liquid crystal layer has a superimposed structure of cholesteric liquid crystal layers different from each other in a helical pitch of the Grandjean orientation.

24. (Previously presented): The method according to claim 13, wherein the reflective polarizing plate comprises a linearly-polarized light separation plate.

25. (Previously presented): The method according to claim 13, wherein the reflective polarizing plate is a circularly-polarized light separation plate.

26. (Currently amended): The polarizing element according to claim ~~7~~ 1, wherein the

polarizing element includes at least one other adhesive layer and the at least one other adhesive layer is not a light diffusion pressure-sensitive adhesive layer.

27. (Previously presented): The polarizing element according to claim 13, wherein the light-diffusion pressure-sensitive adhesive layer is provided directly on the circularly-polarized light separation plate.

28. (Canceled)

29. (Currently amended): The method according to claim ~~28~~ 13, wherein the polarizing element includes at least one other adhesive layer and the at least one other adhesive layer is not a light diffusion pressure-sensitive adhesive layer.

30. (Currently amended): The method according to claim 13, wherein the retardation plate is provided directly on the light-diffusion pressure-sensitive adhesive layer ~~is provided directly on the circularly-polarized light separation plate.~~

31. (Currently amended): The polarizing element according to claim ~~2~~ 1, wherein the polarizing element comprises two light-diffusion pressure-sensitive adhesive layers provided to the reflective polarizing plate.

32. (Currently amended): The polarizing element according to claim ~~2~~ 1, wherein the polarizing element comprises three light-diffusion pressure-sensitive adhesive layers provided to the reflective polarizing plate.

33. (Previously presented): The method according to claim 13, wherein the polarizing element comprises two light-diffusion pressure-sensitive adhesive layers provided to the reflective polarizing plate.

34. (Previously presented): The method according to claim 13, wherein the polarizing element comprises three light-diffusion pressure-sensitive adhesive layers provided to the reflective polarizing plate.